

## SICERSIL 96

### Microsilica (Silica Fume) / Specification

Product	% weight limits	% weight typ.
SiO <sub>2</sub>	> 93.0	95-96 typ.
Al <sub>2</sub> O <sub>3</sub>	< 1.0	< 0,20 typ.
Fe <sub>2</sub> O <sub>3</sub>	< 0.5	< 0.15 typ.
CaO	< 1.0	< 0.50 typ.
Na <sub>2</sub> O	< 0.5	< 0.20 typ.
K <sub>2</sub> O	< 1.5	< 0.80 typ.
Loss on ignition (L.O.I.)		
750 °C		1.00 typ.
Coarse particles > 45 µm (325 mesh)		1-2 typ. (max. 6.0)
pH-value		7.5-9.5
bulk density		Densified approx. 350 – 700 kg/m <sup>3</sup>
packaging		big bags or 10 kg paper bags on pallets

Sicerma GmbH  
Lauerstraße 17  
D-41812 Erkelenz

Fon: +49 2432 933 1252  
Fax: +49 2432 933 3880

sicerma@sicerma.de  
www.sicerma.de

Quality is our priority.

We are certified  
according to  
ISO 9001:2015.