

SICERSIL ZR

Microsilica (ZR Silica Fume) / Specification

Product	% weight/typical	min./max.
SiO ₂	93.0	92-94
ZrO ₂	2.00	
Fe ₂ O ₃	0.35	
Al ₂ O ₃	0.10	
CaO	0.01	0.3 max.
K ₂ O	0.01	
Na ₂ O	0.01	
Loss on ignition (L.O.I.) 1000 °C	0.30 typ.	0.60 max.
D50	approx. 1.8 µm	
pH-value	Approx 3.0	
Bulk density	approx. 350 kg/m ³	
Packaging	600 kg big bags or 25 kg bags on pallets	

Sicerma GmbH
Lauerstraße 17
D-41812 Erkelenz

Fon: +49 2432 933 1252
Fax: +49 2432 933 3880

sicerma@sicerma.de
www.sicerma.de

Quality is our priority.

We are certified
according to
ISO 9001:2015.