

SICERSIL 96

Microsilica (Silica Fume) / Specification

Product	% weight
SiO ₂	96 typ.
C	0,80 typ.
Al ₂ O ₃	0,25 typ.
Fe ₂ O ₃	0,10 typ.
CaO	0,50 typ.
Na ₂ O	0,20 typ.
K ₂ O	0,70 typ.
MgO	0,50 typ.
Loss on ignition (L.O.I.) 1000 °C	2,00 typ.
Coarse particles > 45 µm (325 mesh)	1-2 typ.
pH-value	7,5-9,5
bulk density	Undensified approx. 300-350 kg/m ³ Densified approx. 450-550 kg/m ³
packaging	big bags or 15 kg paper bags on pallets

Sicerma GmbH
Lauerstraße 17
D-41812 Erkelenz

Fon: +49 2432 933 1252
Fax: +49 2432 933 3880

sicerma@sicerma.de
www.sicerma.de

Quality is our priority.

We are certified
according to
ISO 9001:2008.